

italvellido

SCHEDA TECNICA TECHNICAL CARD

Data / Date

26.02.13

| | |
|---|-----------------|
| Articolo / Article / Tkanina | Tokyo |
| Codice Articolo / Article Code / Kod tkaniny | 23049 |
| Composizione / Composition / Kompozycja | 100 % PL |
| Peso Gr/mtl / Weight Grs/lmt / Waga gr/mtb | 672 |
| Altezza cm / Width cms / Szerokość cm | 140 |

Odporność na ścieranie

Test Martindale

Colour degradation after 3000 rubs: 4/5

UNI EN ISO 12947 - 2

100.000 Giri / Rubs / **Cykli**

EN 14465, appendix A

Solidità Luce / Colour Fastness to light / **Odporność kolorów na światło**

UNI EN ISO 105-B02

>4/5

Blue Scale 1/8

Solidità Sfregamento / Colour Fastness to rubbing / **Odporność kolorów na pocieranie**

UNI EN ISO 105-X12

>5 Secco / Dry / **Sucho**

Gray Scale 1/5

>5 Umido / Wet / **Mokro**

Odporność na Pilling

Test Pilling

UNI EN ISO 12945-2

Degradation average photographic scale 1/5:

>5

Manutenzione / Maintenance



Note/Notes: **Dimensional stability to dry washing (UNI EN ISO 3175)**

warp: +/- % weft: +/- %

Dimensional stability to washing (UNI EN ISO 6330)

warp: +/- % weft: +/- %

* The results are tested in the laboratory and they must be considered as indicative.

ITALVELLUTI Polska Sp. z o.o.
33-386 Podegrodzie, Brzezna 495
tel. 18 446 07 84 fax. 18 414 54 51
e-mail: italvelluti@italvelluti.pl
www.italvelluti.eu

italvelluti